

560

Insulating Fiberoid Fish Paper

Thin Vulcanized Cellulose Fiber for most Electrical Insulation

Its qualities of toughness, flexibility, and edge resistance combined with high dielectric strength, and ready absorption of insulating varnish, have led to its predominant use as an IMPROVED motor slot call insulation.

FEATURES:

- THICKNESS: 0.010" ± 10%
- ELECTRICAL STRENGTH: 300 Volts per mil. (typical)
- DENSITY: 1.1 gm per cubic cm min.
- TENSILE STRENGTH: MD 15,000 psi, (typ.) and CD 6000 psi, (typ.)
- BURSTING STRENGTH: (Mullen) 270 psi (typical)
- TEARING STRENGTH: MD 375 grams (typ.) and CD 450 grams (typ.)
- Meets MIL. Spec. MIL-I-695A Type F
- ZINC CHLORIDE CONTENT: 0.05% max.
- Color: Dark Blue-Grey

Product Availability:			
Part No.	DESCRIPTION	Size	
560	Insulating "Fish Paper" - Rolled, 1 per	(10 x 24)"	UPC: 010151151728
560-100	Insulating "Fish Paper" - Flat Sheets, 100 per	(10 x 24)"	UPC: 010151154682



HTS: 3917.39.0000 CoO: Japan

PART No: 560